


CLAIMS


1. Process for the preparation of a polymer composition, the process comprising a step of contacting a polymer that comprises carboxyl groups with a cyclic imino ether compound characterized in that the cyclic imino ether compound is a phenylene oxazine according to formula (I)



(I)

in which formula

R = an oxazine group according to formula (II)



(II)

$n = 0, 1, 2, 3, 4$ or 5

and that the polymer is contacted with said oxazine in an extruder at a temperature above $100\text{ }^{\circ}\text{C}$.

2. Process according to claim 1 wherein the polymer is a (co)polyamide, a (co)polyester or a blend hereof.
3. Process according to any one of claims 1-2, wherein the extruder is a single or a twin screw extruder.
4. Process according to claim 3, wherein the extruder is a single screw extruder.
5. Process according to any one of claims 1-4, wherein the oxazine is 2,2'-phenylene-bis(5, 6-dihydro-4H-1,3-oxazine)
6. Process according to any one of claims 1-5, wherein the concentration of the oxazine is 0.01-5 wt% relative to the amount of the polymer.
7. Use of the polymer composition obtained with the process according to any one of claims 1-6 in applications in aqueous or acid environment, or in coatings.